



TIKKURILA

SISÄ 20

RENOVATION PAINT



DESCRIPTION

Water-borne dispersion paint.

RECOMMENDED USES

Interior walls and ceilings in dry spaces.

PRODUCT FEATURES

For interior painting of concrete, plaster, filler, plasterboard and wood fiberboard surfaces according to instructions. Also suitable for repainting previously painted surfaces.



SISÄ 20

TECHNICAL DATA

Base paints	A BASE, C BASE
Colour Shades	Can be tinted in Tikkurila colors.
Gloss	Semi-matt.
Coverage	Absorbent surfaces 7 - 9 m ² /l. Non-absorbent surfaces 9 - 11 m ² /l.
Can sizes	A BASE: 0.9 l, 2.7 l, 9 l, 18 l C BASE: 0.9 l, 2.7 l, 9 l
Thinner	Water
Application method	Brush, roller or spray. Airless spray application - nozzle 0.018" - 0.023" - thinning 0-10 % by volume.
Drying time	Dust dry in half an hour. Recoatable after 1-2 hours.
Density (kg/l)	Approx. 1.3 kg/l, SFS 3635
Chemical resistance	Resists cleaning chemicals and weak solvents, such as white spirit.
Wet scrub resistance	SFS-EN 13300 class II, ISO 11998
Heat resistance	85 °C, SFS 3757.
Volume solids (%)	35
VOC	(cat A/a) max. 30g/l (2010). Sisä 20 contains VOC max. 30g/l.
Storage	Protect from frost.



SISÄ 20

APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be dry, the temperature of the air at least +5 °C and the relative humidity of the air below 80 %.

Surface preparation

Unpainted surfaces:

Clean the surfaces by removing any dirt and dust. If needed, fill the surfaces with a suitable filler and sand the dried surface. Remove the sanding dust. Prime with, for example, Sisä 2.

Previously painted surfaces:

Wash the surfaces with diluted paint cleaning agent and rinse carefully with water. Sand hard, glossy painted surfaces matt and remove any sanding dust. Fill cracks and holes with a suitable filler and sand the dried surface. Remove the sanding dust. If needed, prime with Sisä 2.

Painting

Stir Sisä 20 well before use and thin with water, if necessary. Apply 1-2 coats with a roller, brush, or spray.

Cleaning of tools

Remove excess paint from tools and wash with water immediately.

Maintenance instructions

The painted surface reaches ultimate durability and hardness in approx. 4 weeks from surface treatment. Avoid cleaning during this period of time.

Clean the surfaces with a cleaning tool and neutral (pH 6 - 8) detergent. Clean very soiled surfaces using mild alkaline (pH 8-10) detergent solution and a cloth, mop or sponge, for example. Rinse the surface well.

Maintenance treatment

Surfaces painted with Sisä 20 can be maintenance painted with the same or similar water-borne paint. See Pretreatment.

Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety

Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.